AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the present application:

Listing of Claims:

1. (**Previously Presented**) A polytetrafluoroethylene block-shaped molded article having a melt viscosity and a block deformation amount contained within a polygonal region surrounded by a straight line A: $x = 1.0 \times 10^9$ (melt viscosity of 1.0×10^9 poise), a straight line B: $x = 2.5 \times 10^{10}$ (melt viscosity of 2.5×10^{10} poise), a straight line C1: $y = 7.0$ (block deformation amount of 7.0%), a straight line D1: $y = 0$ (block deformation amount of 0%), a straight line E1: $y = -8.7\text{Log}_{10}(x) + 91$ in a graph with an x-axis being a common logarithm of the melt viscosity (poise) at 380°C of polytetrafluoroethylene and a y-axis being the block deformation amount (%) which is a weight loss until a stable film or sheet is cut from the molded article,

wherein the polytetrafluoroethylene block-shaped molded article is obtained by compression-molding and baking a polytetrafluoroethylene powder obtained by suspension polymerization, and

said polytetrafluoroethylene block-shaped molded article is cylindrical and has a height of at least 800 mm.

2. (**Previously Presented**) The molded article according to claim 1, wherein the melt viscosity at 380°C of the molded article is at most 2 x 10^{10} poise.

3. (**Previously Presented**) The molded article according to claim 1, wherein the block deformation amount is more than 0.7%.

4. (**Canceled**)

5. (**Withdrawn**) A method of producing a polytetrafluoroethylene block-shaped molded article, comprising inserting a polytetrafluoroethylene preform obtained by compression-molding a polytetrafluoroethylene powder, into a pipe in a state in which a symmetry axis of the preform is horizontal; placing the pipe on two rolls spaced apart in a horizontal direction; and heating the preform to bake the preform while rotating the pipe and the preform by rotating at least one roll to transmit a rotation of the roll to the pipe, whereby giving the polytetrafluoroethylene block-shaped molded article.

6. (**Withdrawn**) The method according to claim 5, wherein a load per unit area at the time of baking the preform is at most 100 g/cm^2.

7. (**Withdrawn**) The method according to claim 5, wherein an expansion of the height of the block-shaped molded article which is generated at the time of producing the polytetrafluoroethylene block-shaped molded article from the preform is at least 6%.

8. (**Withdrawn**) A method of producing a polytetrafluoroethylene block-shaped molded article, comprising inserting a polytetrafluoroethylene preform obtained by compression-molding a polytetrafluoroethylene powder, into a pipe in a state in which a symmetry axis of the preform is horizontal; placing the pipe on two rolls spaced apart in a horizontal direction; and hearing the preform to bake the preform while rotating the pipe and the preform by rotating at least one roll to transmit a rotation of the roll to the pipe, wherein the polytetrafluoroethylene block-shaped molded article is produced and has a melt viscosity and a block deformation amount contained within a polygonal region surrounded by a straight line A: $x = 1.0 \times 10^9$ (melt viscosity of 1.0×10^9 poise), a straight line B: $x = 2.5 \times 10^{10}$ (melt viscosity of 2.5×10^{10} poise), a straight line C1: $y = 7.0$ (block deformation amount of 7.0%), a straight line D1: $y = 0$ (block deformation amount of 0%), and a straight line E1: $y = -8.7\mathrm{Log}_{10}(x) + 91$ in a graph with an x-axis being a common logarithm of the melt viscosity (poise) at 380°C of polytetrafluoroethylene and a y-axis being the block deformation amount (%) which is a weight loss until a stable film or sheet can be cut from the molded article.

9. (**Previously Presented**) The polytetrafluoroethylene block-shaped molded article of claim 1, wherein the polytetrafluoroethylene powder in said polytetrafluoroethylene block-shaped molded article is a copolymer of tetrafluoroethylene and another fluoromonomer.

10. (**Previously Presented**) The polytetrafluoroethylene block-shaped molded article of claim 1, wherein the polytetrafluoroethylene powder in said polytetrafluoroethylene block-shaped molded article is a copolymer of tetrafluoroethylene and another perfluorovinylether of the formula (I):

$CF_2 = CF - OR_f$ (I)

wherein R_f is

a perfluoroalkyl group having 1 to 10 carbon atoms,

a perfluoro(alkoxyalkyl) group having 4 to 9 carbon atoms,

a group represented by the formula (II):



(II)

wherein m is a number of 0 to 4, or

a group represented by the formula (III):



(III)

wherein n is a number of 1 to 4.

11. (**Previously Presented**) The polytetrafluoroethylene block-shaped molded article of claim 1, wherein the polytetrafluoroethylene block-shaped molded article has a roundness degree of not more than 5.0%.

12. (**Previously Presented**) The polytetrafluoroethylene block-shaped molded article of claim 1, wherein the polytetrafluoroethylene block-shaped molded article has a roundness degree of not more than 0.3%.

13. (**Previously Presented**) The polytetrafluoroethylene block-shaped molded article of claim 1, wherein the polytetrafluoroethylene block-shaped molded article has a deformation degree of not more than 15%.

14. (**Previously Presented**) The polytetrafluoroethylene block-shaped molded article of claim 1, wherein the polytetrafluoroethylene block-shaped molded article has a deformation degree of not more than 1.0%.

15. (**Previously Presented**) The polytetrafluoroethylene block-shaped molded article of claim 1, wherein the polytetrafluoroethylene block-shaped molded article has a bend of not more than 2.0%.

16. (**Previously Presented**) The polytetrafluoroethylene block-shaped molded article of claim 1, wherein the polytetrafluoroethylene block-shaped molded article has a bend of not more than 0.1%.

17. (**Previously Presented**) The polytetrafluoroethylene block-shaped molded article of claim 1, wherein the height of said polytetrafluoroethylene block-shaped molded article is 20 cm to 150 cm.

18. (**Currently Amended**) A polytetrafluoroethylene block-shaped molded article, said molded article is produced by a method comprising:

inserting a polytetrafluoroethylene preform obtained by compression-molding a polytetrafluoroethylene powder, into a pipe in a state in which a symmetry axis of the preform is horizontal; placing the pipe on two rolls spaced apart in a horizontal direction; and heating the preform to bake the preform while rotating the pipe and the preform by rotating at least one roll to transmit a rotation of the roll to the pipe, wherein the polytetrafluoroethylene block-shaped molded article is produced, said molded article is cylindrical, has a height of at least 800 mm, and has a melt viscosity and a block deformation amount

contained within a polygonal region surrounded by a straight line A: x = 1.0×10^9 (melt viscosity of 1.0×10^9 poise), a straight line B: x = 2.5×10^{10} (melt viscosity of 2.5×10^{10} poise), a straight line C1: y = 7.0 (block deformation amount of 7.0%), a straight line D1: y = 0 (block deformation amount of 0%), and a straight line E1: $y = -8.7\text{Log}_{10}(x) + 91$ in a graph with an x-axis being a common logarithm of the melt viscosity (poise) at 380°C of polytetrafluoroethylene and a y-axis being the block deformation amount (%) which is a weight loss until a stable film or sheet can be cut from the molded article.

19. (**Canceled**)